

# BOLPHANE® BTT+125

Thin Shrink Film suited for High Speed Machinery

**BTT+125** is ideally suited for equipment where high speed packaging equipment is running. Exceptional shrink characteristics on irregular shaped items. **BTT+125** can be successfully used in applications ranging from multimedia to publishing items as well as office supplies

## Advantages

- Enhanced stiffness for high speed machine compatibility.
- Instant Sealing.
- High shrink characteristics at low temperatures.
- Hot slip properties.
- Excellent optics & appearance.



The “Perfect Fit” for all your packaging film needs.





Technical Properties	Test Unit	Test Method		
			<b>BTT+125</b>	
<b>Presentation</b>				
Gauge			48	
Roll Length Singlewound	FT		11660	
Roll Length Centerfold	FT		5830	
Width Singlewound	in	Min: 4in Max: 78in Increment .25in		
Width Centerfold	in	Min: 5in Max: 40in Increment 1in		
<b>Optical Properties</b>				
Haze	%	ASTM D1003-A	3	
Gloss at 20°		ASTM D2457	114	
<b>Shrinkage Properties</b>			<b>LD*</b>	<b>TD*</b>
Free Shrink at 200°F	%	ATSM D2732	30	38
Free Shrink at 260°F			66	67
<b>Mechanical Properties</b>			<b>LD*</b>	<b>TD*</b>
Stiffness modulus	Mpa	ASTM D882	550	600
Elongation at break	%	ASTM D882	100	110
Tensile strength	Kg/cm <sup>2</sup>	ASTM D882	1150	1100
<b>Barrier Properties</b>				
Water vapor transmission rate (100°F, 95% RH)	g/m <sup>2</sup> ,24hrs	ASTM E96	37	
O2 transmission rate (73°F, 0% RH)	cm <sup>3</sup> /m <sup>2</sup> ,24hrs	ASTM D3985	13000	

## Contact Us

Give us a call for more information about our services and products

**Bolloré Inc**  
60 Louisa Viens Drive  
Dayville, CT 06241

1-800-343-0358

[customer.service@bolloréinc.com](mailto:customer.service@bolloréinc.com)

[sales@bolloréinc.com](mailto:sales@bolloréinc.com)

Visit us on the web at  
[www.bolloréinc.com](http://www.bolloréinc.com)